

PE500 Coloured sheet Technical Data Sheet



the people for plastics

	Norm	Unit	PE 500
Physical properties			
Molecular weight	-	10 ⁶ g/mol	0.5
Density	DIN 53479	g/cm ³	0.95
	ISO 1183		

Mechanical properties			
Yield tension	DIN 53 455	N/mm ²	27
	ISO 527-1		
Elongation at yield	DIN 53 455	%	9
	ISO 527-1		
Elongation at break	DIN 53 455	%	> 600
	ISO 527-1		
Tensile modulus of elasticity	DIN 53 455	N/mm ²	1200
	ISO 527-1		
Ball indentation hardness	DIN 53 456	N/mm ²	50
	ISO 2039		
Charpy impact value	DIN 53 456	KJ/m ²	25
	ISO 179		
Attrition	Sand-Slurry procedure	-	< 400
Coefficient of friction	DIN 53 375	-	0.2
Hardness shore D	DIN 53 505	-	65
	ISO 868		

Thermal properties			
Min. permanent temperature		°C	-60
Max. permanent temperature		°C	80
Thermal length expansion coefficient (23°C - 80°C)	DIN 53 752-A	K ⁻¹	1,5 ... 2x10 ⁻⁴
Thermal conductivity		E / (m x K)	0.4

Additional properties			
Volume resistivity	DIN 53 482	Ohm x cm	> 10 ¹⁴
Absorption of water	DIN 53 492	mg	≤ 0,01
Physiologically stable	BgVV-recommendation III	-	Ja*

These technical values are based on our know-how and experience. We strongly recommend doing application tests because of the different influence of processing. These are typical values, not to be construed as specification, so there are no legal rights depending on this table. Trademark rights have to be respected. Do not hesitate to contact us for any technical information