

# PVC Tube - Technical Data Sheet



the people for plastics

<b>I. Physical Properties</b>			
	<b>Test method</b>	<b>Unit</b>	<b>Value</b>
1. Specific gravity	ISO 1183	g/cm <sup>3</sup>	1,36
2. Water absorption	ISO 62	%	0,2
3. Chemical resistance	-	-	DIN 8061
4. Maximum permissible service temp. (no stronger mechanical stress involved)	-		
Upper temperature limit	-	°C	60
Lower temperature limit	-	°C	15
<b>II. Mechanical Properties</b>			
	<b>Test method</b>	<b>Unit</b>	<b>Value</b>
1. Tensile strength at yield	ISO 527	MPa	55
2. Elongation at yield.	ISO 527	%	3
3. Tensile strength at break	ISO 527	MPa	30
4. Elongation at break	ISO 527	%	> 10
5. Impact strength	ISO 179	kJ/m <sup>2</sup>	no break
6. Notch impact strength	ISO 179	kJ/m <sup>2</sup>	3
7. Ball indentation / Rockwell hardness	ISO 20391	MPa	120
8. ShoreD	DIN 53505		82
9. Flexural strength	ISO 178	MPa	90
10. Modulus of elasticity	ISO 527	MPa	3000
<b>III. Thermal Properties</b>			
	<b>Test method</b>	<b>Unit</b>	<b>Value</b>
1. Vicat softening point VST/B/50	ISO 306	°C	75 <sup>1)</sup>
VST/A/50		°C	-
2. Heat deflection temperature HDT/B	ISO75	°C	72 <sup>2)</sup>
HDT/A		°C	-
3. Coefficient of linear thermal expansion	DIN 53752	K <sup>-1</sup> *10 <sup>4</sup>	0,8
4. Thermal conductivity at 20 °C		W/(m*K)	0,14
<b>IV. Electrical Properties</b>			
	<b>Test method</b>	<b>Unit</b>	<b>Value</b>
1. Volume resistivity	VDE 0303	Ω*cm	>10 <sup>15</sup>
2. Surface resistivity		Ω	≥10 <sup>13</sup>
3. Dielectric constant at 1MHz		-	3
4. Dielectric loss factor at 1 MHz	DIN 53483	-	0,01
5. Dielectric strength	VDE 0303	kV/mm	20-40
6. Tracking resistance	IEC 60112		KB 600
<b>V. Additional Data</b>			
	<b>Test method</b>	<b>Unit</b>	<b>Value</b>
1. Bond ability		-	+
2. Friction coefficient	DIN 53375	-	0,6
3. Flammability	UL 94	-	V0
4. UV stabilisation	-	-	Fair

<sup>1)</sup> 65 (solid rod 160 200mm Ø) 57 (solid rod 220 300mm Ø) <sup>2)</sup> 59 (solid rod 160 200mm Ø) 51 (solid rod 220 300mm Ø)  
All values are attributes of the used raw materials.

The physical data contained in this table are typical values. They are obtained on test specimens under specific conditions and represent average values of a large number of tests. The results obtained on this tests specimens cannot be applied to finished parts without reservations, as behaviour is influenced by processing and shaping. Reproduction only with our definite permission.

# PVC Tube - Technical Data Sheet



<sup>1)</sup> 65 (solid rod 160 200mm  $\varnothing$ ) 57 (solid rod 220 300mm  $\varnothing$ ) <sup>2)</sup> 59 (solid rod 160 200mm  $\varnothing$ ) 51 (solid rod 220 300mm  $\varnothing$ )  
All values are attributes of the used raw materials.

The physical data contained in this table are typical values. They are obtained on test specimens under specific conditions and represent average values of a large number of tests. The results obtained on this tests specimens cannot be applied to finished parts without reservations, as behaviour is influenced by processing and shaping. Reproduction only with our definite permission.