

PC Rod - Technical Data Sheet



the people for plastics

Physical Properties	Value	Unit	Method of verification
Density	1.20	g/cm ³	ISO 1183
Moisture pick-up till saturation (in normal climate 23 °C)	0.15	%	ISO 62
Water absorption till saturation (in water at 23 °C)	0.35	%	ISO 62

Mechanical properties	Value	Unit	Method of verification
Tensile stress at yield (v = 50 mm/min):	75	N/mm ²	ISO 527-2
Tensile stress at break (v = 5 mm/min):	-	N/mm ²	ISO 527-2
Nominal percentage elongation at break	> 50	%	ISO 527-2
Tensile modulus of elasticity:	2400	N/mm ²	ISO 527-2
Flexural modulus of elasticity	2400	N/mm ²	ISO 178
Ball indentation hardness (value at 30 s):	120	N/mm ²	ISO 2039-1
Rockwell hardness:	M 75	-	ISO 2039-2
Charpy impact strength (23°C) :	n. br. **	kJ/m ²	ISO 179/1eU
Charpy impact strength - notched (23 °C)	9	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Method of verification
Temperature for using in air (maximum):	130	°C	Max. short term
Temperature for using in air (maximum):	120	°C	Max. lasting
Temperature for using in air (minimum):	-60	°C	-
Heat distortion temperature (HDT A process):	130	°C	ISO 75-2
Coefficient of linear expansion, at length (23-60)°C :	0.65·10 ⁻⁴	1/K	DIN 53752
Thermal conductivity (23 °C):	0.21	W/(K·m)	DIN 52612
Flammability according UL standard:	HB	Grade	UL 94
Vicat softening temperature (VST/B/50):	150	°C	ISO 306
Melting point DSC (10 K/min):	-	°C	ISO 3146

Electrical properties	Value	Unit	Method of verification
Specific volume resistivity:	1013	Ω·m	IEC 60093
Specific surface resistivity	1015	Ω	IEC 60093
Dielectric factor (at 1 MHz)*:	2.9	-	IEC 60250
Dielectric factor (at 100 Hz)*:	3.0	-	IEC 60250
Dissipation factor (at 1 MHz)*:	0.009	-	IEC 60250
Dissipation factor (at 100 Hz)*:	0.006	-	IEC 60250
Dielectric strength K20/K20:	29	kV/mm	IEC 60243-1
Comparative tracking index (CTI):	225	-	IEC 60112

* Values do not apply to black coloured qualities

** n. br. = no break