



U-PVC Sheet Pressed

Grey (RAL 7011)

U-PVC is rated self-extinguishing, has excellent chemical resistance with high mechanical and tensile strength, together with a high degree of stability. U-PVC is easily weldable but has a limited operating temperature range of 0°C to +60°C.

product information

Name:	Unplasticised Polyvinyl Chloride
Other names:	PVC-CAW, GEHR PVC-U
Abbreviation:	U-PVC

key characteristics

- » Machines well to a polished finish
- » Solvent Cemented & Welded
- » Relatively less expensive than other plastics
- » Strong and stiff
- » Flame retardant grades available
- » Chemical resistant
- » Self extinguishing
- » UV stabilised grades available
- » Drinking water approved
- » Food compliant grades available

applications

- » Corrosive fluid handling
- » Valves
- » Tanks
- » Water applications
- » Air conditioning & ventilation systems

this document contains

- » Technical Datasheet (Page 1)
- » Chemical Datasheet (Page 2)
- » Safety Datasheet (Pages 3-4)

For any further information regarding food, fire and water certificates then please contact the sales team on 0116 232 1010

Head Office - Leicester

68 Scudamore Road, Braunstone Frith Industrial Estate, Leicester LE3 1UA
 Telephone / 0116 232 1010
 Fax / 0116 287 3577
 Email / sales@oadbyplastics.co.uk
 Web / www.oadbyplastics.co.uk

U-PVC Sheet Pressed

Grey (RAL 7011)



technical properties

Physical Properties	Test	Unit	Result
1. Specific gravity	ISO 1183	g/cm ³	1.44
2. Maximum service temp. Upper temp limit (no stronger mechanical stress involved)	-	°C	60
Lower temp limit	-	°C	0
Mechanical Properties	Test	Unit	Result
1. Elongation at yield	SO 527	%	4
2. Yield Stress	ISO 527	MPa	58
3. Impact strength	ISO 179	kJ/m ²	-
4. Notch impact strength	ISO 179	kJ/m ²	4
5. Ball indentation	ISO 2039-1	MPa	82
6. Shore-D	ISO 868	-	-
7. Modulus of elasticity	ISO 527	MPa	3300
Thermal Properties	Test Method	Unit	Result
1. Coefficient of linear thermal expansion	DIN 53752	K ⁻¹	0.8 x 10 ⁻⁴
2. Thermal conductivity	DIN 52612	W/(m*K)	0.159
Electrical Properties	Test Method	Unit	Result
1. Surface resistivity	IEC 6093	Ω	10 ¹³
2. Dielectric strength	IEC 60243-1	kV/mm	39
Additional Data	Test Method	Unit	Result
1. Bondability	-	-	-
2. Food compliance	FDA	-	+
3. Flammability	UL 94	-	V-0

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

Key:

Yes	Limited	No or no data
+	o	-

U-PVC Sheet Pressed Grey (RAL 7011)



chemical properties

Agent	Conc %	Working Temp	
		20°C	60°C
Acetic Acid	100	+	-
Acetone	100	-	-
Ammonia	Conc.	+	o
Ammonium chloride		+	+
Amyl Alcohol		+	o
Benzene		-	-
Bleaching Solution	12,5 Cl	+	-
Boric Acid	100	+	o
Brake Fluid		+	+
Butyl Acetate		-	-
Calcium Chloride		+	+
Carbon disulphide	100	-	-
Carbon Tetrachloride		-	-
Chlorine, gas	100	o	-
Chlorobenzene	100	-	-
Chloroform		-	-
Citric Acid	10	+	+
Cresol		-	-
Cyclohexanone	100	-	-
Cyclohexene	100	+	o
Diesel Fuel		+	o
Diethylene oxide, THF		-	-
Ethyl acetate	100	-	-
Ethyl alcohol	96	+	o
Ethylene Chloride	100	-	-
Formic Acid	10	+	o
Frost protection agent	Petrol	+	+
Fuel, aromatic free		+	+
Glycerine	100	+	+
Glycol	100	+	+
Heating oil		+	+
Heptane	100	+	+
Hydrochloric acid	conc.	+	+

Agent	Conc %	Working Temp	
		20°C	60°C
Hydrofluoric acid	40	+	o
Hydrogen peroxide	10	+	+
Hydrogen Sulphide		+	+
Isopropyl Alcohol	100	+	+
Mercurochrome		o	-
Methyl alcohol	100	+	+/o
Methyl ethyl ketone	100	-	-
Methylene chloride	100	-	-
Nitric acid	50	+	+
Nitrobenzine		-	+
Oxalic Acid		+	+
Ozone, gas	ca. 0,5 ppm	+	+
Paraffin Oil	100	+	o
Perchlorethylene		-	-
Petroleum	100	+	+
Petroleum, aromatic free	100	+	+
Phenol, aqu	ca.9	o	-
Phosphoric Acid	50	+	+
Potassium hydroxide liquor	50	+	+
Propyl alcohol		+	o
Pyridine		-	-
Silicone oil		+	+
Sodium carbonate. aqu		+	+
Sodium chloride, aqu		+	+
Sodium Hydroxide liquor	15	o	o
Sodium Hydroxide liquor	60	o	o
Sodium hydrogen sulphite		+	+
Sodium nitrate, aqu		+	+
Sodium thiosulfate		+	+
Sulphuric Acid	96	+	+/o
Tetrahydrofuran	100	-	-
Toluene	100	-	-
Trichlorethylene	100	-	-
Xylene		-	-

Key:

Resistant	Partly Resistant	Non-Resistant
+	o	-

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

U-PVC Sheet Pressed Grey (RAL 7011)



safety properties

Substance/preparation and Company detail

Polyvinylchloride

Oadby Plastics
68 Scudamore Road,
Braunstone Frith Industrial Estate,
Leicester,
LE3 1UA
0116 232 1010

Composition / Indications to components

Chemical characteristics: polymer of vinyl chloride
CAS-number: not necessary

Possible dangers

Unknown

First-aid measures

General comment: medical aid is not necessary
First-aid measures: none
Routes of exposure: none
Symptoms / effects: none

Fire-fighting measures

In case of fire please use gas mask and breathing equipment in depending of circulating air. Fire residues must be disposed of according to the local instructions. Suitable fire-fighting appliance: water fog, foam, fire fighting powder, carbon dioxide
Hazard warning notice: not applicable

Measures in case of unintended release

Person-related measures: none
Environmental protection measures: not applicable
Cleaning equipment: not applicable
Unsuitable cleaning products: not applicable

Handling and storage

Handling: no special regulations must be observed
Storage: unlimited good storage property

Limitation of exposition

Special design of techn. processing facilities: not required
Tolerance levels: none
Exposure measurement procedures: none
Respiratory protection: not required
Eye protection: not required
Body protection: not required

Physical and chemical characteristics

Phenotype

Phenotype / form: semi-finished product, solid state
Colour: dark grey
Smell: not applicable

Change of state

Flash point: not applicable

Other remarks

Density: 1.44 g/cm³

safety properties

Stability and reactivity

Thermal decomposition: above appr. 200°C

Dangerous decomposition products:

Besides hydrochloric acid also carbon dioxide and water will develop during the burning process. In case of incomplete burning also carbon monoxide and traces of phosgene may arise.

Use of stabilisers: none

Exothermic reactions: none

Notices regarding state of aggregation: none

Conditions to be avoided: none

Substances/media to be avoided: none

Toxic information

During several years of usage no effects being harmful for the health were observed.

Ecological information

No biodegradation, no solubility in water, no effects being harmful to the environment must be expected.

Mobility: not applicable

Accumulation: not applicable

Eco-toxicity: not applicable

Waste-disposal information

Can be recycled or can be disposed of together with household rubbish (acc. To local regulations).

Waste key for the unused product: EAK-Code 120 105

Waste name: waste of polyvinylchloride

Transport information

No dangerous product in respect to / according to transport regulations

Notice/symbol transport containers: none

Special marking for containers: none

Regulations

Marking according to GefStoffV/EG: no obligation for marking

Water danger class: class 0 (self classification)

Domestic requirements to be observed: none

Further information

The information is based on our current knowledge. They are meant to describe our products in respect to safety requirements. They do not represent any guarantee of the described product in the sense of the legal guarantee regulations.