



Product information

Product full identity:

Polyoxymethylene Copolymer

Extruded Acetal C offers high stiffness, tensile strength and surface hardness. Acetal C is more resistant against hydrolysis, strong alkalis and thermal-oxidative degradation than Acetal H. This material is food compliant.

Properties

- » Better to machine than all Nylons
- » 10% better properties than Homopolymer, in hot waters
- » Good UV resistance in black
- » Low absorption and dimensional stability
- » Food Compliant

Applications

- » Seals
- » Gears
- » Marine
- » Insulators
- » Medical instrument handles
- » Steam cleaning
- » Bearings
- » Impellers

This document contains

- » Technical Datasheet (Page 2)
- » Chemical Datasheet (Page 3)
- » Safety Datasheet (Pages 4-5)

For any further information regarding food, fire and water certificates then please contact the sales team on 0116 232 1010

Technical Properties

Physical Properties	Test	Unit	Result
1. Specific gravity	ISO 1183	g/cm ³	1.41
2. Water absorption	ISO 62	%	0.8
3. Maximum service temp. Upper temp limit - Short Term (no stronger mechanical stress involved)	-	°C	140
	-	°C	105
5. Lower temp limit	-	°C	-40
Mechanical Properties	Test	Unit	Result
1. Tensile stress at yield	ISO 527-2	MPa	63
2. Elongation at yield	ISO 527-2	%	-
3. Tensile strength at break	ISO 527-2	MPa	63
4. Elongation at break	ISO 527-2	%	31
5. Impact strength	ISO 179-1/1eU	kJ/m ²	220
6. Notch impact strength	ISO 179-1/1eA	kJ/m ²	8
7. Ball indentation / Rockwell hardness	ISO 2039-1/-2	MPa	140 / M84
8. Shore-D	-	-	-
9. Flexural modulus of elasticity	ISO 178	MPa	2500
10. Tensile modulus of elasticity	ISO 527	MPa	2600
Thermal Properties	Test Method	Unit	Result
1. Vicat-softening point VST/B/50	ISO 306	°C	150
2. Heat deflection temperature HDT/A	ISO 75-2	°C	96
3. Coefficient of linear thermal expansion	ISO 11359	k ⁻¹ *10 ⁻⁴	1.1
4. Thermal conductivity at 23 °C	DIN 52612	W/(m*K)	0.31
Electrical Properties	Test Method	Unit	Result
1. Volume resistivity	VDE 0303	Ω x m	-
2. Surface resistivity	IEC 6093	Ω	10 ¹³
3. Dielectric constant at 1MHz	IEC 60250	-	3.8
4. Dielectric dissipation factor at 1 MHz	IEC 60250	10 ⁶ Hz	0.008
5. Electrical strength	IEC 60243-1	kV/mm	20
6. Comparative tracking index (CTI)	IEC 60112	-	600
Additional Data	Test Method	Unit	Result
1. Bondability	-	-	-
2. Food compliance	FDA	-	+
3. Flammability	UL 94	-	HB

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

Key:

Yes	Limited	No data
+	0	-

Chemical Properties

Agent	Conc %	Working Temp		Agent	Conc %	Working Temp	
		20°C	60°C				
Acetic Acid	100	o	-	Hydrofluoric acid	40	-	
Acetone	100	+	o	Hydrogen peroxide	10	+	-
Ammonia	Conc.	+	+	Hydrogen Sulphide		+	
Ammonium chloride		+	o	Isopropyl Alcohol	100	+	+
Amyl Alcohol		+/o		Mercurochrome		-	
Benzene		+	o	Methyl alcohol	100	+	+
Bleaching Solution	12,5 Cl	o	-	Methyl ethyl ketone	100	o	o
Boric Acid	100	-	-	Methylene chloride	100	-	-
Brake Fluid		o/-		Nitric acid	50	-	-
Butyl Acetate		+	o	Nitrobenzine		o	
Calcium Chloride		+	+	Oxalic Acid		-	
Carbon disulphide	100	+	+	Ozone, gas	ca. 0,5 ppm	-	-
Carbon Tetrachloride		+	o	Paraffin Oil	100	+	+
Chlorine, gas	100			Perchlroethylene		+	o
Chlorobenzene	100	o	o	Petroleum	100	+	
Chloroform		/	-	Petroleum, aromatic free	100	+	+
Citric Acid	10	o	-	Phenol, aqu	ca.9	-	-
Cresol				Phosphoric Acid	50	-	-
Cyclohexanone	100	+		Potassium hydroxide liquor	50	o	
Cyclohexene	100	+		Propyl alcohol			
Diesel Fuel		+	+	Pyridine			
Diethylene oxide, THF		o	o	Silicone oil		+	+
Ethyl acetate	100	+	o	Sodium carbonate, aqu		+	+
Ethyl alcohol	96			Sodium chloride, aqu		+	+
Ethylene Chloride	100	+	-	Sodium Hydroxide liquor	15	+	o
Formic Acid	10	+		Sodium Hydroxide liquor	60	o	
Frost protection agent	Petrol	+	+	Sodium hydrogen sulphite		-	-
Fuel, aromatic free		+	o	Sodium nitrate, aqu		+	+
Glycerine	100	+	+	Sodium thiosulfate			
Glycol	100	+	+	Sulphuric Acid	96	-	-
Heating oil		-	-	Tetrahydrofurance	100	o	o
Heptane	100	-	-	Toluene	100	+	+
Hydrochloric acid	conc.	-	-	Trichlorethylene	100	-	-
				Xylene		-	-

Safety Properties

Substance / preparation and company detail

Acetal-Copolymer
Oadby Plastics
68 Scudamore Road,
Braunstone Frith Industrial Estate,
Leicester,
LE3 1UA
0116 232 1010

Composition / indications to components

Chemical characterization : Polyoxymethylene-Copolymer (POM-C)

Hazardous substances : Product contains no hazardous ingredients liable to be disclosed.

Possible dangers

Classification : Not classified

Physical/ chemical hazards : Flammable

Health risks : Dust can cause mechanical irritation.

Hazards for the environment: Based on our information, there is no danger to the environment.

The product is according to Directive 1999/45/EC and its annexes are not classified as dangerous.

First-aid measures

General information : The product is being classified as non-toxic.

In case of inhalation : In case the plastic burns and combustion gases are inhaled, remove person to fresh air and keep warm and get medical help if necessary.

In case of skin contact : Burns caused by molten material on skin need to be rapidly cooled down with water; do not attempt removal of plastic without medical assistance. If irritation develops, seek medical attention.

In case of eye contact : Flush eyes well with copious quantities of water. Seek medical attention, if irritation persists.

In case of ingestion : The product is non-toxic; no first aid procedures are required.

Fire-fighting measures

Suitable extinguishing media : Water, foam, gaseous and dry extinguishing media

Particular endangerments by : Hazardous combustion products may emerge, apart from harmless

Fire fighting and hazardous Water (H₂O); carbon dioxide (CO₂), carbon monoxide (CO) and combustion products oxygen how hydrogen cyanide (HCN). Formation of further decomposition and oxidation products depends upon the fire conditions. Under special fire conditions traces of other toxic substances are possible. Fire fighting: Approved pressure demand breathing apparatus and protective clothing should be used for all fires. Additional Information: Residues after the fire, after appropriate rules dispose.

Marking and transport information

Personal precautions : N/A

Environmental precaution : N/A

Methods for cleaning up : Mechanical removal

Handling and storage

Advice on safe handling: During machining of the stock shapes, evacuate swarf to prevent slipping or tripping.

Storage: Store inert product dry and cool. Keep storage and working areas sufficiently ventilated. Keep away from source of flame, heat and ignition. Due to the risk of collapsing, do not stack more than 2 pallets on to of each other. Pallets should not stack on to of each other along aisles.

Safety Properties

Limitation of exposition

Ingredients with : CAS-Nr. 50-00-0 (Formaldehyde)

Occupational exposure Occupational exposure limit (TRGS 900) 0,5 ml/m³ 0,62 mg/m³

Limits to be monitored High limit / Exceedance factor = 1

Limit values can be fractionally under run by adequate ventilation

The MAK-Wert for Formaldehyde (TRGS 900) was abrogated with the amendment in January 2006. This information only serves as a benchmark.

General protection : Keep the workplace sufficiently ventilated

Hygiene measures : Eating and drinking are not allowed.

Continuous supply of fresh air to the workplace together with removal of processing fumes through exhaust systems is recommended. Avoid breathing in gaseous degradation products and dust that may result by material overheating.

Hand protection : Safety gloves in case of contact with warm material

Eye protection : Safety goggles or shield during machining

Body protection : Working clothes

Respiratory protection : Adequate ventilation at workplace is required

Physical and chemical characteristics

Aggregate : solid

Colour : product-specific

Odour : slight, product specific

Safety related facts

Boiling point : N/A

Melting point : 160 - 175 °C (DIN/EN/ISO 3146)

Corrosion temperature : N/A

Flash point : N/A

Self ignition temperature : 320 - 340 °C (ASTM D1929)

Explosion hazard or limit : non explosive

Oxidizing characteristics : None

Density (20 °C) : 1.41 g/cm³ (ISO 1183)

Solubility (in Water 20 °C) : insoluble

Viscosity : N/A

Additional Information : None

Stability and reactivity

Conditions to avoid : Temperatures above melting point

Material to avoid : Strong oxidant

Hazardous decomposition: Formaldehyde CAS-Nr. 50-00-0

Products : Carbon monoxide CAS-Nr. 630-08-0

Do not machine together with PVC or other polymers which contain halogenated flame retardants.

Toxic information

Toxicology : Based on our experience and information available, no adverse health effects are expected if handled as recommended with suitable precautions for designated uses.

Primary Irritation on skin : N/A

Primary Irritation on eyes : N/A

Sensitization : not known

Practical Tests : N/A

Additional information : N/A

Ecological information

The material does not harm the environment but is not biologically degradable.

Safety Properties

Waste-disposal information

The product must be disposed in accordance with the local authorities.

Transport information

The product must be disposed in accordance with the local authorities.

Regulations

The product does not require a hazard warning label in accordance with EC directives.

Further information

The information is based on our current knowledge. They are meant to describe our products in respect to safety requirements. They do not represent any guarantee of the described product in the sense of the legal guarantee regulations.