



## Product information

---

### Product full identity:

Anti-Static Ultra-High Molecular Weight Polyethylene

PE1000 EL (10<sup>-4</sup> Ω) has an improved electrical conductivity value against PE1000 AST (10<sup>-8</sup> Ω). By incorporating an effective carbon black grade PE1000 EL offers the electrostatic dissipative properties often required for sensitive applications.

## Properties

---

- » Permanently antistatic and conductive
- » Volume resistance <10<sup>-4</sup> Ω
- » Stabilized against UV rays
- » Food compliant
- » ATEX 95 - conform

## Applications

---

- » General mechanical engineering
- » Sliding and conveyor elements
- » Guide for belt drives
- » Material lining
- » Areas with explosion hazards
- » High machine speeds in dry and dusty areas

## This document contains

---

- » Technical Datasheet (Page 2)
- » Chemical Datasheet (Page 3)
- » Safety Datasheet (Pages 4-5)

For any further information regarding food, fire and water certificates then please contact the sales team on 0116 232 1010

## Technical Properties

Physical Properties	Test	Unit	Result
1. Specific gravity	ISO 1183-1	g/cm <sup>3</sup>	0.93
2. Water absorption till saturation 23°C	-	%	0.1
3. Maximum service temp. Upper temp limit - Short Term (no stronger mechanical stress involved)	-	°C	120
Long Term	-	°C	85
5. Lower temp limit	-	°C	-100
Mechanical Properties	Test	Unit	Result
1. Tensile strength at yield	ISO 527	MPa	>18
2. Elongation at yield	ISO 527	%	16
3. Abrasion (sand slurry test)	ISO 5527	%	>110
4. Elongation	ISO 527	%	>350
5. Impact strength	ISO 179	kJ/m <sup>2</sup>	no break
6. Notch impact strength	ISO 179	kJ/m <sup>2</sup>	>140
7. Ball indentation	ISO 2039-1	MPa	38
8. Shore-D	DIN 53505	-	64
9. Modulus of elasticity	ISO 527	MPa	700
Thermal Properties	Test Method	Unit	Result
1. Vicat-softening point	ISO 306	°C	80
2. Coefficient of linear thermal expansion	ISO 11359	%-1	1.5-2 10 <sup>-4</sup>
3. Thermal conductivity	DIN 52612	W/(m*K)	>0.4
Electrical Properties	Test Method	Unit	Result
1. Surface resistivity	IEC 6093	Ω	10 <sup>4</sup>
2. Dielectric strength	IEC 60243	kV/mm	-
Additional Data	Test Method	Unit	Result
1. Bondability	-	-	-
2. Food compliance	FDA	-	+
3. Flammability	UL 94	-	HB

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

### Key:

Yes	Limited	No data
+	o	-

## Chemical Properties

Agent	Conc %	Working Temp		Agent	Conc %	Working	Temp
		20°C	60°C				
Acetic Acid	100	+		Hydrofluoric acid	40	+	o
Acetone	100	+	+/o	Hydrogen peroxide	10	+	+
Ammonia	Conc.	+	+	Hydrogen Sulphide		+	
Ammonium chloride		+	+	Isopropyl Alcohol	100	+	+
Amyl Alcohol		+	+	Mercurochrome		+	
Benzene		+	+/o	Methyl alcohol	100	+	+
Bleaching Solution	12,5 Cl			Methyl ethyl ketone	100	+	
Boric Acid	100	+	+	Methylene chloride	100	o/-	-
Brake Fluid		+	+	Nitric acid	10	+	+
Butyl Acetate		+		Nitric acid	50	o	o/-
Calcium Chloride		+	+	Nitrobenzine		+	
Carbon disulphide	100			Oxalic Acid		+	+
Carbon Tetrachloride				Ozone, gas	ca. 0,5 ppm	+/o	-
Chlorine, gas	100			Paraffin Oil	100	+	+
Chlorobenzene	100			Perchlorethylene		o	-
Chloroform				Petroleum	100	+	o
Citric Acid	10	+	+	Petroleum, aromatic free	100		
Cresol		+	+	Phenol, aqu	ca.9	+	+
Cyclohexanone	100	+		Phosphoric Acid	50	+	+
Cyclohexene	100	+	+	Potassium hydroxide liquor	50	+	+
Diesel Fuel		+	+	Propyl alcohol		+	+
Ethyl acetate	100	+		Pyridine		+	
Ethyl alcohol	96	+	+	Silicone oil		+	+
Ethylene Chloride	100			Sodium carbonate, aqu		+	+
Formic Acid	10	+	+	Sodium chloride, aqu		+	+
Frost protection agent		+	+	Sodium Hydroxide liquor	60	+	+
Fuel, aromatic free		+	+	Sodium hydrogen sulphite		+	+
Glycerine	100	+	+	Sodium nitrate, aqu		+	+
Glycol	100	+	+	Sodium thiosulfate		+	+
Heating oil		+	+	Sulphuric Acid	96	o	-
Heptane	100	-	-	Tetrahydrofuran	100		
Hydrochloric acid	10	+	+	Toluene	100		
Hydrochloric acid	conc.	+	+	Trichlorethylene	100	-	-
				Xylene		-	-

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

### Key:

Yes	Limited	No data
+	o	-

## Safety Properties

### Substance / preparation and company detail

Polyethylene EL  
Oadby Plastics  
68 Scudamore Road,  
Braunstone Frith Industrial Estate,  
Leicester,  
LE3 1UA  
0116 232 1010

### Composition / indications to components

Chemical characteristics: polymer of ethylene  
CAS-number: not necessary

### Possible dangers

Unknown

### First-aid measures

General comment: medical aid is not necessary  
First-aid measures: none  
Routes of exposure: none  
Symptoms / effects: none

### First-fighting measures

Suitable fire-fighting appliance: water fog, foam, fire fighting powder, carbon dioxide  
Hazard warning notice: not applicable

### Measures in case of unintended release

Person-related measures: none  
Environmental protection measures: not applicable  
Cleaning equipment: not applicable  
Unsuitable cleaning products: not applicable

### Handling and storage

Handling: no special regulations must be observed  
Storage: unlimited good storage property

### Limitation of exposition

Special design of techn. processing facilities: not required  
Tolerance levels: none  
Exposure measurement procedures: none  
Respiratory protection: not required  
Eye protection: not required  
Body protection: not required

### Physical and chemical characteristics

#### Phenotype

Phenotype / form: semi-finished product, solid state  
Colour: black  
Smell: not applicable

#### Change of state

Crystalline melting range: 130-135 °C  
Flash point: not applicable

#### Other remarks

Density: 0.945 g/cm<sup>3</sup>

## Safety Properties

### Stability and reactivity

Thermal decomposition : above appr. 300 °C

Dangerous decomposition products :

Besides carbon black also carbon dioxide and water as well as low molecular parts of PE will develop during the burning process. In case of incomplete burning also carbon monoxide may arise.

Use of stabilisers : none

Exothermic reactions : none

Notices regarding state of aggregation : none

Conditions to be avoided : none

Substances/media to be avoided : none

### Toxic information

During several years of usage no effects being harmful for the health were observed.

### Ecological information

No biodegradation, no solubility in water, no effects being harmful to the environment must be expected.

Mobility: not applicable

Accumulation: not applicable

Eco-toxicity: not applicable

### Waste-disposal information

Can be recycled or can be disposed of together with household rubbish (acc. To local regulations).

Waste key for the unused product: EAK-Code 120 105

Waste name: waste of Polyolefine.

### Transport information

No dangerous product in respect to / according to transport regulations

Notice/symbol transport containers: none

Special marking for containers: none

### Regulations

Marking according to GefStoffV/EG: no obligation for marking

Water danger class: class 0 (self classification)

Domestic requirements to be observed: none

### Further information

The information is based on our current knowledge. They are meant to describe our products in respect to safety requirements. They do not represent any guarantee of the described product in the sense of the legal guarantee regulations.