



U-PVC Foam Sheet Extruded

White / black / blue / green / grey / red / yellow

U-PVC Foam is rated self-extinguishing, very light weight (SG 0.5 - 0.7), durable and versatile. U-PVC Foam due to its surface structure is ideal for all print media; this product also boasts low sound and thermal conductivity.

product information

Name:	Free-foamed PVC
Other names:	Ongrofoam
Abbreviation:	Foam PVC

key characteristics

- » Light weight
- » Low water absorption
- » Indoor and outdoor use
- » Excellend sound and heat isolation properties
- » Self-extinghuising
- » Smooth surface

applications

- » Exhibition boards and signs
- » Interior decorations and wall cladding
- » Displays
- » Letter cut
- » Screen printing
- » Digital printing

this document contains

- » Technical Datasheet (Page 1)
- » Chemical Datasheet (Page 2)
- » Safety Datasheet (Pages 3-6)

For any furthur information regarding food, fire and water certificates then please contact the sales team on 0116 232 1010

Head Office - Leicester
68 Scudamore Road, Braunstone Frith Industrial Estate, Leicester LE3 1UA
Telephone / 0116 232 1010
Fax / 0116 287 3577
Email / sales@oadbyplastics.co.uk
Web / www.oadbyplastics.co.uk

U-PVC Foam Sheet Extruded

White / Black / Blue / Green / Grey / Red / Yellow



technical properties

Physical Properties	Test	Unit	Result
1. Specific gravity	ISO 1183	g/cm ³	0.5
2. Water absorption	ISO 62	%	<1
3. Maximum service temp. Upper temp limit (no stronger mechanical stress involved)	-	°C	60
Lower temp limit	-	°C	0

Mechanical Properties	Test	Unit	Result
1. Tensile strength at yield	ISO 527	MPa	>12
2. Elongation at yield	ISO 527	%	-
3. Tensile strength at break	ISO 527	MPa	-
4. Elongation at break	ISO 527	%	15
5. Impact strength	ISO 179	kJ/m ²	12
6. Notch impact strength	ISO 179	kJ/m ²	-
7. Ball indentation / Rockwell hardness	ISO 2039-1	MPa	-
8. Shore-D	DIN 53505	-	>40
9. Flexural strength	ISO 178	MPa	-
10. Modulus of elasticity	ISO 527	MPa	>750

Thermal Properties	Test Method	Unit	Result
1. Vicat-softening point VST/B/50	ISO 306	°C	72
2. Heat deflection temperature HDT/B	ISO 75	°C	-
HDT/A	-	°C	-
3. Coefficient of linear thermal expansion	DIN 53752	k ⁻¹ *10 ⁻⁴	0.75
4. Thermal conductivity at 20 °C	DIN 52612	W/(m*K)	0.08

Electrical Properties	Test Method	Unit	Result
1. Volume resistivity	VDE 0303	Ω x m	-
2. Surface resistivity	-	Ω	>5 x 10 ¹⁴
3. Dielectric constant at 1MHz	-	-	-
4. Dielectric loss factor at 1 MHz	DIN 53483	-	-
5. Dielectric strength	VDE 0303	kV/mm	13
6. Tracking resistance	IEC 60112	-	-

Additional Data	Test Method	Unit	Result
1. Bondability	-	-	-
2. Food compliance	FDA	-	-
3. Flammability	UL 94	-	V-0

Key:

Yes	Limited	No or no data
+	o	-

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

U-PVC Foam Sheet Extruded

White / Black / Blue / Green / Grey / Red / Yellow



chemical properties

Agent	Conc %	Working Temp	
		20°C	60°C
Acetic Acid	100		
Acetone	100		
Ammonia	Conc.		
Ammonium chloride			
Amyl Alcohol			
Benzene			
Bleaching Solution	12,5 Cl		
Boric Acid	100		
Brake Fluid			
Butyl Acetate			
Calcium Chloride			
Carbon disulphide	100		
Carbon Tetrachloride			
Chlorine, gas	100		
Chlorobenzene	100		
Chloroform			
Citric Acid	10		
Cresol			
Cyclohexanone	100		
Cyclohexene	100		
Diesel Fuel			
Diethylene oxide, THF			
Ethyl acetate	100		
Ethyl alcohol	96		
Ethylene Chloride	100		
Formic Acid	10		
Frost protection agent	Petrol		
Fuel, aromatic free			
Glycerine	100		
Glycol	100		
Heating oil			
Heptane	100		
Hydrochloric acid	conc.		

Agent	Conc %	Working Temp
Hydrofluoric acid	40	
Hydrogen peroxide	10	
Hydrogen Sulphide		
Isopropyl Alcohol	100	
Mercurochrome		
Methyl alcohol	100	
Methyl ethyl ketone	100	
Methylene chloride	100	
Nitric acid	50	
Nitrobenzine		
Oxalic Acid		
Ozone, gas	ca. 0,5 ppm	
Paraffin Oil	100	
Perchloroethylene		
Petroleum	100	
Petroleum, aromatic free	100	
Phenol, aqu	ca.9	
Phosphoric Acid	50	
Potassium hydroxide liquor	50	
Propyl alcohol		
Pyridine		
Silicone oil		
Sodium carbonate. aqu		
Sodium chloride, aqu		
Sodium Hydroxide liquor	15	
Sodium Hydroxide liquor	60	
Sodium hydrogen sulphite		
Sodium nitrate, aqu		
Sodium thiosulfate		
Sulphuric Acid	96	
Tetrahydrofuran	100	
Toluene	100	
Trichloroethylene	100	
Xylene		

Key:

Resistant	Partly Resistant	Non-Resistant
+	o	-

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

U-PVC Foam Sheet Extruded

White / Black / Blue / Green / Grey / Red / Yellow



safety properties

Substance/preparation and Company detail

Product Name : Polyvinyl Chloride foam
Material Name : Polyvinyl Chloride Homopolymer
CAS Number : 9002-86-2
Material Synonyms : PVC
NFPA Ratings : Health=1, Fire=0, Reactivity=0
Oadby Plastics
68 Scudamore Road,
Braunstone Frith Industrial Estate,
Leicester,
LE3 1UA
0116 232 1010

Composition / Indications to components

Tin stabilized PVC sheets, 2.5% by weight metal-tin or tin-mercaptide based stabilizer.
Pigments and additives used to enhance specific properties are encapsulated in the polymer resin matrix.
No solvents. No plasticizers. No cadmium, lead, or other heavy metals used.

Possible dangers

No particular hazards known.
Health Hazard Data
Effects of a Single Overexposure
Swallowing: Non-relevant
Skin absorption: Non-relevant
Inhalation: Non-relevant
Skin contact: Exposure is not expected to cause adverse health effects
Eye contact: Non-relevant
Effects of a Repeated Overexposure: None currently known
Medical Conditions Aggravated by Overexposure: None currently known
Other Effects of Overexposure: None currently known

First-aid measures

In general handling the material will not cause accidents.
Inhalation
If exposed to combustion fumes in high concentration - bring victim to fresh air. Medical attention needed.
Skin Contact
Burns resulting from accidental contact with molten material must be flushed immediately with cold water.
Do not remove the polymer from the skin. Medical attention needed.
Eye Contact
Like any foreign body, can cause mechanical irritation. Consult physician.

Fire-fighting measures

Extinguishing Media
Water spray or CO₂. CO₂ is less recommended due to lack of cooling capacity.
Special Fire Fighting Procedures
Personnel without suitable respiratory apparatus should leave the affected area to prevent exposure to toxic or combustible gases.
Special Protective Equipment for Fire-fighters
Positive-pressure self-contained breathing apparatus, protective clothing, gas mask approved for acid vapours.
Unusual Fire and Explosion Hazards
PVC is a self extinguishing fire retardant material that being exposed to open fire and high temperatures decomposes emitting large quantities of HCl, which tends to extinguish the flames.
It does not continue to burn after ignition without an external fire source.
HCl has a strong acidic odour that causes sensory alert at very low concentrations. HCl odour threshold = 0.77 ppm.
Exposure to high concentrations of HCl will cause irritation of the respiratory passages, at very high concentrations may cause burns to mucous membranes.
Soot emitted when PVC is forced to burn may obscure visibility.
No special precautions and no personal protective equipment needed.

U-PVC Foam Sheet Extruded

White / Black / Blue / Green / Grey / Red / Yellow



safety properties

Measures in case of unintended release

No special precautions and no personal protective equipment needed. Collect mechanically for disposal or recovery.

Handling and storage

General handling precautions

Avoid contact with eyes.

Ventilation

General (mechanical) room ventilation is expected to be satisfactory where this product is stored and handled.

Other precautions

No explosion hazard. In the event of fire, cool and overlap product with water.

Static electricity discharge sparks possible during handling. Avoid contact or vicinity of flammable materials.

When opening truck or railcar for unloading, ventilate before entering.

Storage

Store in a cool shady area. No special technical protective measures required.

Limitation of exposition

Respiratory protection: No special protection needed

Hand protection/protection gloves: No special protection needed

Eye protection: No special protection needed

Other protective equipment: No special protection needed

Physical and chemical characteristics

Appearance: Flat sheets

Physical State: Solid

Colour: White or coloured

Odour: None

Density: 0,55- 0,70 gr/cm³

Heat Deflection: 62-65°C

Boiling Point, 760 Hg: Not relevant

Viscosity: Not relevant

Solubility in Water: <0.1g/100mL at 23°C

pH Value: Not relevant

Flammability Limit: None

Explosion Limits: None

Evaporation Rate: Not relevant

Percent Volatiles: Not relevant

Stability and reactivity

Stability

Stable.

Conditions to avoid

Excessive heat, or open flame. Temperature above 150 °C will decompose raw polymer resin and liberate HCl.

Incompatible materials

Oxidizing agents or strong mineral acids can cause reaction.

Thermal decomposition

Begins above 150°C caused by fire, overheating during improper processing. Fumes damaging to health may be released.

Hazardous decomposition products

Burning can produce the following combustion products:

Carbon monoxide (CO) - is highly toxic if inhaled;

Carbon dioxide (CO₂) - in sufficient concentrations can act as an asphyxiant;

Hydrogen chloride (HCl) - in high concentrations cause irritation of the respiratory passages, at very high concentrations may cause burns to mucous membranes.

Reactivity

Hazardous polymerization: Will not occur

Hazardous reactions: None

U-PVC Foam Sheet Extruded

White / Black / Blue / Green / Grey / Red / Yellow



safety properties

Toxic information

PVC materials have a very low acute toxicity. In rats an acute LD50 > 10 gr/kg of body weight. PNEUMOCONIOSIS has been described from inhalation of combustion products (effects of overexposure).

Industrial hygiene studies have shown that under normal and expected conditions of use of PVC materials, exposures are well below applicable limits.

Acute Toxicological Information

Acute oral toxicity: None

Acute percutaneous toxicity: None

Acute vapour exposure: None

Primary skin irritation: No irritation

Eye irritation: No irritation

Sensitization: No information available

Chronic effects: Unknown

Carcinogenicity: None

Other Toxicological Information

No known toxicological effects with normal use. For heating see section 10.

Additional Information

No additional toxicity information currently available.

Ecological information

Persistence and Degradability

Detailed studies have not been conducted concerning the environmental fate of the product. According to present knowledge no unfavourable ecological effects are to be expected.

Not generally hazardous to water. Insoluble in water, non-toxic solid.

Mobility: No information currently available

Persistence and biodegradability: Biodegradation period - tens of years.

Bio accumulative potential: No information currently available.

Environmental Risks

No hazard expectation to terrestrial or aquatic flora and fauna.

Eco-toxicity: LD50 (rats) > 10 gr/kg

: IC50 (bacterial inhibition) - no data available

Aquatic toxicity: LC50 (daphnia magna) - no data available

: LC50 (fathead minnow – fish) - no data available

Other information

All available ecological data have been taken into account for the development of the hazard and precautionary information contained in this safety data.

Waste-disposal information

The product is not considered hazardous under current EPA hazardous waste regulations.

Recycling is the preferred method of disposal.

Alternatively, the product may be disposed of in an approved landfill.

High temperature incineration under controlled conditions due to formation of HCl.

All wastes should be evaluated in conjunction with applicable solid and hazardous waste regulations, Toxicity

Characteristic

Leaching Procedures (TCLP), and disposed of as appropriate.

This product does not contain any cadmium or other heavy metal pigments or stabilizers.

It is the user's responsibility to dispose of all wastes in accordance with all national and local regulations at properly permitted or authorized facilities.

Transport information

Additional transportation data: Not currently regulated under Department of Transportation regulations

Labelling: No labelling is required in accordance with the EEC directives

Placarding: No placarding is required in accordance with the EEC directives

Special transport requirements : None

Packaging: Avoid dark-coloured packaging to prevent heat distortion

The product is classified as a non-hazardous material in the meaning of transport regulations.

U-PVC Foam Sheet Extruded

White / Black / Blue / Green / Grey / Red / Yellow



safety properties

Regulations

With regards to dust formed as a consequence of mechanical treatments, the appropriate regulations value limits for fine dust must be observed: MAC value (fine dust) – 5mg/m³.

OSHA Hazard Communication Classification for dusts and combustion fumes: Irritant, Skin Hazard, and Lung Hazard.

SARA Title III Classification for dusts and combustion fumes: Acute Health Hazard; Chronic Health Hazard.

WHMIS Classification: Non-hazardous

Further information

The information is based on our current knowledge. They are meant to describe our products in respect to safety requirements. They do not represent any guarantee of the described product in the sense of the legal guarantee regulations.